



Collection - Antica | Finish - Matte  
Possible graphics - 4 | Recycled content - 17 %

**Packing and weights**

| Pieces/Box |      | Boxes/Pallet |       | weight |        |           |
|------------|------|--------------|-------|--------|--------|-----------|
| unit       | m2   | Boxes        | m2    | Kg/m2  | Kg/Box | Kg/Pallet |
| 13         | 1.44 | 51           | 73.44 | 12.80  | 18.40  | 958       |



|  | Test  | Value/Standard Tolerance                             | Typical Product Value * | Test Standard   |
|--|---|--|-------------------------|-----------------|
|  | <b>Dimensional Characteristics</b>                    |  |                         |                 |
|  | Length and Width                                      | ± 0.5%   MAX. ± 2mm                                  | Guaranteed   Guaranteed |                 |
|  | Orthogonality   | ± 0.5%   MAX. ± 2mm                                  | Guaranteed              |                 |
|  | Straightness  | ± 0.5%   MAX. ± 1.5mm                                | Guaranteed              | EN ISO 10545-2  |
|  | Flatness  | + 0.5% / - 0.3%   MAX. +2 / - 1.5mm                  | Guaranteed              |                 |
|  | Thickness   | ± 5%   MAX. ± 0.5mm                                  | Guaranteed              |                 |
|  | <b>Water Absorption</b>                               | E > 10%  | 16% <= E <= 19%         | EN ISO 10545-3  |
|  | <b>Linear Expansion</b>                               |  | <= 7.00E-06 / °C        | EN ISO 10545-8  |
|  | <b>Thermal Shock Resistance</b>                       | Test upon request                                    |                         | EN ISO 10545-9  |
|  | <b>Crazing Resistance</b>                             | Required   | Guaranteed              | EN ISO 10545-11 |
|  | <b>Lead Release</b>                                   | For special surfaces (for instance, kitchen counter) | Test upon request       | EN ISO 10545-15 |
|  | <b>Rupture Modulus N/mm2   Breaking Strength in N</b> | => 15N/mm2   => 600N                                 | => 16N/mm2   => 600N    | EN ISO 10545-4  |

|  | Test  | Chemical Product             | Value/Standard Tolerance  | Typical Product Value *      | Test Standard   |
|--|---|------------------------------|---|------------------------------|-----------------|
|  | <b>Resistance to acids and bases (high and low concentrations)</b>      | Hydrochloric acid (18%)      |   | To be confirmed case by case |                 |
|  |   | Lactic acid (5%)             |   | To be confirmed case by case |                 |
|  |   | Potassium hydroxide (100g/l) | <small>To report classification for low concentrations of acids and alkalis / Optional for high concentrations of acids and alkalis</small> | To be confirmed case by case |                 |
|  |   | Hydrochloric acid (3%)       |   | To be confirmed case by case | EN ISO 10545-13 |
|  |   | Citric acid (100g/l)         |   | To be confirmed case by case |                 |
|  |   | Potassium hydroxide (30g/l)  |   | To be confirmed case by case |                 |
|  | <b>Resistance to cleaning products<br/>Resistance to pool additives</b> | ammonium chloride (100g/l)   |   | Guaranteed                   |                 |
|  |   | Sodium hypochlorite (20mg/l) | Minimum Class B   | Guaranteed                   |                 |
|  | <b>Stain Resistance</b>   | Olive Oil                    |   | Guaranteed                   |                 |
|  |   | Green Chromium/Iron oxide    | Minimum Class 3   | Guaranteed                   | EN ISO 10545-14 |
|  |   | Iodine                       |   | Guaranteed                   |                 |

\* Indicative value

It is guaranteed the compliance with the values required by norm EN 14411. Typical Pavigrés reference value is merely indicative, which can vary from real data, and does not have the purpose of any trading proposal.