



Collection - Cargemma | Finish - Matte

Shade variation - V2 | Possible graphics - 15 | Recycled content - 17 %

Packing and weights

Pieces/Box		Boxes/Pallet		weight		
unit	m2	Boxes	m2	Kg/m2	Kg/Box	Kg/Pallet
10	1.18	64	75.52	15.30	18.10	1,178



	Test	Value/Standard Tolerance	Typical Product Value *	Test Standard	
	Dimensional Characteristics				
	Length and Width	± 0.5% MAX. ± 2mm	Guaranteed Guaranteed		
	Orthogonality	± 0.5% MAX. ± 2mm	Guaranteed		
	Straightness	± 0.5% MAX. ± 1.5mm	Guaranteed	EN ISO 10545-2	
	Flatness	+ 0.5% / - 0.3% MAX. +2 / - 1.5mm	Guaranteed		
	Thickness	± 5% MAX. ± 0.5mm	Guaranteed		
	Water Absorption	E > 10%	16% <= E <= 19%	EN ISO 10545-3	
	Linear Expansion		<= 7.00E-06 / °C	EN ISO 10545-8	
	Thermal Shock Resistance		Test upon request	EN ISO 10545-9	
	Crazing Resistance		Required	Guaranteed	EN ISO 10545-11
	Lead Release		For special surfaces (for instance, kitchen counter)	Test upon request	EN ISO 10545-15
	Rupture Modulus N/mm2 Breaking Strength in N		=> 15N/mm2 => 600N	=> 16N/mm2 => 600N	EN ISO 10545-4

	Test	Chemical Product	Value/Standard Tolerance	Typical Product Value *	Test Standard
	Resistance to acids and bases (high and low concentrations)	Hydrochloric acid (18%)		To be confirmed case by case	
		Lactic acid (5%)		To be confirmed case by case	
		Potassium hydroxide (100g/l)		To be confirmed case by case	
		Hydrochloric acid (3%)	<small>To report classification for low concentrations of acids and alkalis / Optional for high concentrations of acids and alkalis</small>	To be confirmed case by case	EN ISO 10545-13
		Citric acid (100g/l)		To be confirmed case by case	
		Potassium hydroxide (30g/l)		To be confirmed case by case	
	Resistance to cleaning products Resistance to pool additives	ammonium chloride (100g/l)		Guaranteed	
		Sodium hypochlorite (20mg/l)	Minimum Class B	Guaranteed	
	Stain Resistance	Olive Oil		Guaranteed	
		Green Chromium/Iron oxide	Minimum Class 3	Guaranteed	EN ISO 10545-14
		Iodine		Guaranteed	

* Indicative value

It is guaranteed the compliance with the values required by norm EN 14411. Typical Pavigrés reference value is merely indicative, which can vary from real data, and does not have the purpose of any trading proposal.