



Collection - Glade | Finish - Anti-slip Rectified  
Shade variation - V2 | Possible graphics - 18



**Packing and weights**

Pieces/Box		Boxes/Pallet		weight		
unit	m2	Boxes	m2	Kg/m2	Kg/Box	Kg/Pallet
3	1.07	40	42.80	21.30	22.80	932

	Test	Value/Standard Tolerance	Typical Product Value *	Test Standard		
	<b>Length and Width</b>	± 0.6%   MAX. ± 2mm	± 0.1%   ± 0.1%			
	<b>Orthogonality</b>	± 0.5%   MAX. ± 2mm	± 0.3%			
	<b>Straightness</b>	± 0.5%   MAX. ± 1.5mm	± 0.3%	EN ISO 10545-2		
	<b>Flatness</b>	± 0.5%   MAX. ± 2mm	± 0.3%			
	<b>Thickness</b>	± 5%   MAX. ± 0.5mm	± 3%   MAX. ± 0.4mm			
	<b>Water Absorption</b>	E ≤ 0.5%	E ≤ 0.1%	EN ISO 10545-3		
	<b>Linear Expansion</b>		≤ 7.00E-06 / °C	EN ISO 10545-8		
	<b>Thermal Shock Resistance</b>	Resistant		EN ISO 10545-9		
	<b>Crazing Resistance</b>	Required	Guaranteed	EN ISO 10545-11		
	<b>Frost Resistance</b>	Must not produce noticeable alterations to surface	Resistant	EN ISO 10545-12		
	<b>Lead Release</b>	For special surfaces (for instance, kitchen counter)	Test upon request	EN ISO 10545-15		
	<b>Rupture Modulus N/mm2   Breaking Strength in N</b>	=> 35N/mm2   => 1300N	=> 45N/mm2 / => 460Kg/cm2   => 2100N	EN ISO 10545-4		
	<b>Test</b>	<b>Chemical Product</b>	<b>Value/Standard Tolerance</b>	<b>Typical Product Value *</b>	<b>Test Standard</b>	
		Hydrochloric acid (18%)		To be confirmed case by case		
		Lactic acid (5%)		To be confirmed case by case		
	<b>Resistance to acids and bases (high and low concentrations)</b>		Potassium hydroxide (100g/l)		To be confirmed case by case	
			Hydrochloric acid (3%)		To be confirmed case by case	EN ISO 10545-13
			Citric acid (100g/l)		To be confirmed case by case	
			Potassium hydroxide (30g/l)		To be confirmed case by case	
	<b>Resistance to cleaning products</b>	ammonium chloride (100g/l)	Minimum Class B	Guaranteed		
	<b>Resistance to pool additives</b>	Sodium hypochlorite (20mg/l)		Guaranteed		
	<b>Stain Resistance</b>	Olive Oil		Guaranteed		
		Green Chromium/Iron oxide	Minimum Class 3	Guaranteed	EN ISO 10545-14	
		Iodine		Guaranteed		
	<b>Slip Resistance **</b>	DIN EN16165 (Anexo A) - C   DIN EN16165 (Anexo B) - R11				

\* Indicative value

\*\* Tests carried out by certified external laboratories whose results are available upon request at head office. Pavigrés is available to prove in our own laboratories the technical characteristics of any purchased lot upon request. Anti-slip performance is guaranteed at the time of delivery of the product.

It is guaranteed the compliance with the values required by norm EN 14411. Typical Pavigrés reference value is merely indicative, which can vary from real data, and does not have the purpose of any trading proposal.