




Collection - Next Pro | Finish - Matte Rectified

Nr. of Possible Different Faces: 1

Shade variation - V2 | Possible graphics - 12 | Recycled content - 32 %


Packing and weights

Pieces/Box		Boxes/Pallet		weight		
unit	m2	Boxes	m2	Kg/m2	Kg/Box	Kg/Pallet
2	1.58	30	47.40	21.90	34.60	1,069



	Test	Value/Standard Tolerance	Typical Product Value *	Test Standard
	Length and Width	± 0.6% MAX. ± 2mm	± 0.1% ± 0.1%	
	Orthogonality	± 0.5% MAX. ± 2mm	± 0.3%	
	Straightness	± 0.5% MAX. ± 1.5mm	± 0.3%	EN ISO 10545-2
	Flatness	± 0.5% MAX. ± 2mm	± 0.3%	
	Thickness	± 5% MAX. ± 0.5mm	± 3% MAX. ± 0.4mm	

Dimensional Characteristics



Water Absorption	E ≤ 0.5%	E ≤ 0.1%	EN ISO 10545-3
Deep Abrasion	≤ 175 mm3	130 mm3	EN ISO 10545-6
Linear Expansion		≤ 7.00E-06 / °C	EN ISO 10545-8
Thermal Shock Resistance	Resistant		EN ISO 10545-9
Frost Resistance	Must not produce noticeable alterations to surface	Resistant	EN ISO 10545-12
Lead Release	For special surfaces (for instance, kitchen counter)	Test upon request	EN ISO 10545-15
Rupture Modulus N/mm2 Breaking Strength in N	⇒ 35N/mm2 ⇒ 1300N	⇒ 45N/mm2 / ⇒ 460Kg/cm2 ⇒ 2100N	EN ISO 10545-4

Test	Chemical Product	Value/Standard Tolerance	Typical Product Value *	Test Standard
	Hydrochloric acid (18%)		To be confirmed case by case	
	Lactic acid (5%)		To be confirmed case by case	
	Potassium hydroxide (100g/l)		To be confirmed case by case	
	Hydrochloric acid (3%)		To be confirmed case by case	EN ISO 10545-13
	Citric acid (100g/l)		To be confirmed case by case	
	Potassium hydroxide (30g/l)		To be confirmed case by case	
	ammonium chloride (100g/l)	Minimum Class B	Guaranteed	
	Sodium hypochlorite (20mg/l)		Guaranteed	

Resistance to acids and bases (high and low concentrations)

**Resistance to cleaning products
Resistance to pool additives**

	Olive Oil		≥ Class 2	
	Green Chromium/Iron oxide	Declare Value	≥ Class 2	EN ISO 10545-14
	Iodine		≥ Class 2	

	Slip Resistance **	DIN EN16165 (Anexo A) - B DIN EN16165 (Anexo B) - R10
--	---------------------------	---

* Indicative value

** Tests carried out by certified external laboratories whose results are available upon request at head office. Pavigrés is available to prove in our own laboratories the technical characteristics of any purchased lot upon request. Anti-slip performance is guaranteed at the time of delivery of the product.

It is guaranteed the compliance with the values required by norm EN 14411. Typical Pavigrés reference value is merely indicative, which can vary from real data, and does not have the purpose of any trading proposal.