



Collection - Glade | Finish - Matte
Possible graphics - 18



Packing and weights

Pieces/Box		Boxes/Pallet		weight		
unit	m2	Boxes	m2	Kg/m2	Kg/Box	Kg/Pallet
4	1.43	40	57.20	14.70	21.00	860

	Test	Value/Standard Tolerance	Typical Product Value *	Test Standard
	Dimensional Characteristics			
	Length and Width	± 0.6% MAX. ± 2mm	± 0.3% ± 0.3%	
	Orthogonality	± 0.5% MAX. ± 2mm	± 0.3%	
	Straightness	± 0.5% MAX. ± 1.5mm	± 0.3%	EN ISO 10545-2
	Flatness	± 0.5% MAX. ± 2mm	± 0.3%	
	Thickness	± 5% MAX. ± 0.5mm	± 3% MAX. ± 0.4mm	
	Water Absorption	E ≤ 0.5%	E ≤ 0.1%	EN ISO 10545-3
	Linear Expansion		≤ 7.00E-06 / °C	EN ISO 10545-8
	Thermal Shock Resistance	Resistant		EN ISO 10545-9
	Crazing Resistance	Required	Guaranteed	EN ISO 10545-11
	Frost Resistance	Must not produce noticeable alterations to surface	Resistant	EN ISO 10545-12
	Lead Release	For special surfaces (for instance, kitchen counter)	Test upon request	EN ISO 10545-15
	Rupture Modulus N/mm2 Breaking Strength in N	⇒ 35N/mm2 ⇒ 700N	⇒ 45N/mm2 / ⇒ 460Kg/cm2 ⇒ 1100N	EN ISO 10545-4

	Test	Chemical Product	Value/Standard Tolerance	Typical Product Value *	Test Standard
	Resistance to acids and bases (high and low concentrations)	Hydrochloric acid (18%)		To be confirmed case by case	
		Lactic acid (5%)		To be confirmed case by case	
		Potassium hydroxide (100g/l)	<small>To report classification for low concentrations of acids and alkalis / Optional for high concentrations of acids and alkalis</small>	To be confirmed case by case	
		Hydrochloric acid (3%)		To be confirmed case by case	EN ISO 10545-13
		Citric acid (100g/l)		To be confirmed case by case	
		Potassium hydroxide (30g/l)		To be confirmed case by case	
	Resistance to cleaning products Resistance to pool additives	ammonium chloride (100g/l)	Minimum Class B	Guaranteed	
		Sodium hypochlorite (20mg/l)		Guaranteed	
	Stain Resistance	Olive Oil		Guaranteed	
		Green Chromium/Iron oxide	Minimum Class 3	Guaranteed	EN ISO 10545-14
		Iodine		Guaranteed	
	Slip Resistance **		Test upon request	To be confirmed for each ref.	

* Indicative value

** Tests carried out by certified external laboratories whose results are available upon request at head office. Pavigrés is available to prove in our own laboratories the technical characteristics of any purchased lot upon request. Anti-slip performance is guaranteed at the time of delivery of the product.

It is guaranteed the compliance with the values required by norm EN 14411. Typical Pavigrés reference value is merely indicative, which can vary from real data, and does not have the purpose of any trading proposal.